PROHLÁŠENÍ O VLASTNOSTECH

č. **4 - 018 - 160107 - 2021/02** **CZ**

1.) Jedinečný identifikační kód typu výrobku:

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete (033)

2.) Zamýšlené/zamýšlená použití:

Lepená kotva pro použití v betonu

3.) Výrobce:

EJOT Baubefestigungen GmbH, In der Stockwiese 35, 57334 Bad Laasphe - Germany

4.) Systém/systémy POSV:

Systém 1

5.)

Evropský dokument pro posuzování:	**EAD 330499-01-0601**
Evropské technické posouzení:	**ETA-16/0107**
Subjekt pro technické posuzování:	**DIBt - Deutsches Institut für Bautechnik, Berlin**
Oznámený subjekt/oznámené subjekty:	**2873 - IFSW - Technische Universität Darmstadt**

6.) Deklarovaná vlastnost/Deklarované vlastnosti:

a) Mechanická odolnost a stabilita (BWR 1) a bezpečnost a dostupnost (BWR 4)

základní charakteristiky	vlastnosti výrobku
Charakteristická odolnost proti zatížení tahem (statické a kvazistatické zatížení)	Viz přílohy C 1 až C 3, C 5, C 7.
Charakteristická odolnost proti smykovému zatížení (statické a kvazistatické zatížení)	Viz příloha C 1, C 4, C 6, C 8.
Posuny (statické a kvazistatické zatížení)	Viz příloha C 9 až C 11
Charakteristická odolnost a posuny pro kategorie seismické odolnosti C1	Viz příloha C 12 až C 16

PROHLÁŠENÍ O VLASTNOSTECH

č. **4 - 018 - 160107 - 2021/02** **CZ**

EJOT®

b) Bezpečnost při požáru (BWR 2)

základní charakteristiky	vlastnosti výrobku

c) Hygiena, zdraví a životní prostředí (BWR 3)

základní charakteristiky	vlastnosti výrobku

d) Ochrana proti hluku (BWR 5)

základní charakteristiky	vlastnosti výrobku

e) Úspora energie a zadržování tepla (BWR 6)

základní charakteristiky	vlastnosti výrobku

f) Udržitelné využívání přírodních zdrojů (BWR 7)

základní charakteristiky	vlastnosti výrobku

Vlastnosti výše uvedeného výrobku jsou ve shodě se souborem deklarovaných vlastností. Toto prohlášení o vlastnostech se v souladu s nařízením (EU) č. 305/2011 vydává na výhradní odpovědnost výrobce uvedeného výše.

Podepsáno za výrobce a jeho jménem:

Dr. Jens Weber
(jméno)

Bad Laasphe, 27 January 2021
(místo a datum vydání)

(podpis)

Table C1: Characteristic values for steel tension resistance and steel shear resistance of threaded rods

Size				M8	M10	M12	M16	M20	M24	M27	M30
Cross section area		A_s	[mm²]	36,6	58	84,3	157	245	353	459	561
Characteristic tension resistance, Steel failure [1]											
Steel, Property class 4.6 and 4.8		$N_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63	98	141	184	224
Steel, Property class 5.6 and 5.8		$N_{Rk,s}$	[kN]	18 (17)	29 (27)	42	78	122	176	230	280
Steel, Property class 8.8		$N_{Rk,s}$	[kN]	29 (27)	46 (43)	67	125	196	282	368	449
Stainless steel A2, A4 and HCR, class 50		$N_{Rk,s}$	[kN]	18	29	42	79	123	177	230	281
Stainless steel A2, A4 and HCR, class 70		$N_{Rk,s}$	[kN]	26	41	59	110	171	247	-[3]	-[3]
Stainless steel A4 and HCR, class 80		$N_{Rk,s}$	[kN]	29	46	67	126	196	282	-[3]	-[3]
Characteristic tension resistance, Partial factor [2]											
Steel, Property class 4.6 and 5.6		$\gamma_{Ms,N}$	[-]	2,0							
Steel, Property class 4.8, 5.8 and 8.8		$\gamma_{Ms,N}$	[-]	1,5							
Stainless steel A2, A4 and HCR, class 50		$\gamma_{Ms,N}$	[-]	2,86							
Stainless steel A2, A4 and HCR, class 70		$\gamma_{Ms,N}$	[-]	1,87							
Stainless steel A4 and HCR, class 80		$\gamma_{Ms,N}$	[-]	1,6							
Characteristic shear resistance, Steel failure [1]											
Without lever arm	Steel, Property class 4.6 and 4.8	$V^0_{Rk,s}$	[kN]	9 (8)	14 (13)	20	38	59	85	110	135
	Steel, Property class 5.6 and 5.8	$V^0_{Rk,s}$	[kN]	11 (10)	17 (16)	25	47	74	106	138	168
	Steel, Property class 8.8	$V^0_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63	98	141	184	224
	Stainless steel A2, A4 and HCR, class 50	$V^0_{Rk,s}$	[kN]	9	15	21	39	61	88	115	140
	Stainless steel A2, A4 and HCR, class 70	$V^0_{Rk,s}$	[kN]	13	20	30	55	86	124	-[3]	-[3]
	Stainless steel A4 and HCR, class 80	$V^0_{Rk,s}$	[kN]	15	23	34	63	98	141	-[3]	-[3]
With lever arm	Steel, Property class 4.6 and 4.8	$M^0_{Rk,s}$	[Nm]	15 (13)	30 (27)	52	133	260	449	666	900
	Steel, Property class 5.6 and 5.8	$M^0_{Rk,s}$	[Nm]	19 (16)	37 (33)	65	166	324	560	833	1123
	Steel, Property class 8.8	$M^0_{Rk,s}$	[Nm]	30 (26)	60 (53)	105	266	519	896	1333	1797
	Stainless steel A2, A4 and HCR, class 50	$M^0_{Rk,s}$	[Nm]	19	37	66	167	325	561	832	1125
	Stainless steel A2, A4 and HCR, class 70	$M^0_{Rk,s}$	[Nm]	26	52	92	232	454	784	-[3]	-[3]
	Stainless steel A4 and HCR, class 80	$M^0_{Rk,s}$	[Nm]	30	59	105	266	519	896	-[3]	-[3]
Characteristic shear resistance, Partial factor [2]											
Steel, Property class 4.6 and 5.6		$\gamma_{Ms,V}$	[-]	1,67							
Steel, Property class 4.8, 5.8 and 8.8		$\gamma_{Ms,V}$	[-]	1,25							
Stainless steel A2, A4 and HCR, class 50		$\gamma_{Ms,V}$	[-]	2,38							
Stainless steel A2, A4 and HCR, class 70		$\gamma_{Ms,V}$	[-]	1,56							
Stainless steel A4 and HCR, class 80		$\gamma_{Ms,V}$	[-]	1,33							

[1] Values are only valid for the given stress area A_s. Values in brackets are valid for undersized threaded rods with smaller stress area A_s for hot-dip galvanised threaded rods according to EN ISO 10684:2004+AC:2009.
[2] in absence of national regulation
[3] Anchor type not part of the ETA

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete

Performances
Characteristic values for steel tension resistance and steel shear resistance of threaded rods

Annex C 1

Table C2: Characteristic values for Concrete cone failure and Splitting with all kind of action

Anchor size				**All Anchor types and sizes**
Concrete cone failure				
Non-cracked concrete		$k_{ucr,N}$	[-]	11,0
Cracked concrete		$k_{cr,N}$	[-]	7,7
Edge distance		$c_{cr,N}$	[mm]	1,5 h_{ef}
Axial distance		$s_{cr,N}$	[mm]	2 $c_{cr,N}$
Splitting				
Edge distance	$h/h_{ef} \geq 2,0$	$c_{cr,sp}$	[mm]	1,0 h_{ef}
	$2,0 > h/h_{ef} > 1,3$			$2 \cdot h_{ef} \left(2,5 - \frac{h}{h_{ef}} \right)$
	$h/h_{ef} \leq 1,3$			2,4 h_{ef}
Axial distance		$s_{cr,sp}$	[mm]	2 $c_{cr,sp}$

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete	**Annex C 2**
Performances Characteristic values for Concrete cone failure and Splitting with all kind of action	

Table C3: Characteristic values of tension loads under static and quasi-static action

Anchor size threaded rod					**M8**	**M10**	**M12**	**M16**	**M20**	**M24**	**M27**	**M30**
Steel failure												
Characteristic tension resistance			$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$ (or see Table C1)							
Partial factor			$\gamma_{Ms,N}$	[-]	see Table C1							
Combined pull-out and concrete failure												
Characteristic bond resistance in non-cracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	10	12	12	12	12	11	10	9
	II: 80°C/50°C				7,5	9	9	9	9	8,5	7,5	6,5
	III: 120°C/72°C				5,5	6,5	6,5	6,5	6,5	6,5	5,5	5,0
	I: 40°C/24°C	flooded bore hole			7,5	8,5	8,5	8,5	No Performance Assessed			
	II: 80°C/50°C				5,5	6,5	6,5	6,5				
	III: 120°C/72°C				4,0	5,0	5,0	5,0				
Characteristic bond resistance in cracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	4,0	5,0	5,5	5,5	5,5	5,5	6,5	6,5
	II: 80°C/50°C				2,5	3,5	4,0	4,0	4,0	4,0	4,5	4,5
	III: 120°C/72°C				2,0	2,5	3,0	3,0	3,0	3,0	3,5	3,5
	I: 40°C/24°C	flooded bore hole			4,0	4,0	5,5	5,5	No Performance Assessed			
	II: 80°C/50°C				2,5	3,0	4,0	4,0				
	III: 120°C/72°C				2,0	2,5	3,0	3,0				
Reduktion factor ψ^0_{sus} in cracked and non-cracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,73							
	II: 80°C/50°C				0,65							
	III: 120°C/72°C				0,57							
Increasing factors for concrete ψ_c			C25/30		1,02							
			C30/37		1,04							
			C35/45		1,07							
			C40/50		1,08							
			C45/55		1,09							
			C50/60		1,10							
Concrete cone failure												
Relevant parameter					see Table C2							
Splitting												
Relevant parameter					see Table C2							
Installation factor												
for dry and wet concrete			γ_{inst}	[-]	1,0	1,2						
for flooded bore hole					1,4				No Performance Assessed			

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete	**Annex C 3**
Performances Characteristic values of tension loads under static and quasi-static action	

Table C4: Characteristic values of shear loads under static and quasi-static action

Anchor size threaded rod			**M8**	**M10**	**M12**	**M16**	**M20**	**M24**	**M27**	**M30**
Steel failure without lever arm										
Characteristic shear resistance Steel, strength class 4.6, 4.8, 5.6 and 5.8	$V^0_{Rk,s}$	[kN]	$0,6 \cdot A_s \cdot f_{uk}$ (or see Table C1)							
Characteristic shear resistance Steel, strength class 8.8 Stainless Steel A2, A4 and HCR, all classes	$V^0_{Rk,s}$	[kN]	$0.5 \cdot A_s \cdot f_{uk}$ (or see Table C1)							
Partial factor	$\gamma_{Ms,V}$	[-]	see Table C1							
Ductility factor	k_7	[-]	1,0							
Steel failure with lever arm										
Characteristic bending moment	$M^0_{Rk,s}$	[Nm]	$1,2 \cdot W_{el} \cdot f_{uk}$ (or see Table C1)							
Elastic section modulus	W_{el}	[mm³]	31	62	109	277	541	935	1387	1874
Partial factor	$\gamma_{Ms,V}$	[-]	see Table C1							
Concrete pry-out failure										
Factor	k_8	[-]	2,0							
Installation factor	γ_{inst}	[-]	1,0							
Concrete edge failure										
Effective length of fastener	l_f	[mm]	$\min(h_{ef};\ 12 \cdot d_{nom})$						$\min(h_{ef};\ 300mm)$	
Outside diameter of fastener	d_{nom}	[mm]	8	10	12	16	20	24	27	30
Installation factor	γ_{inst}	[-]	1,0							

Table C5: Characteristic values of tension loads under static and quasi-static action

Anchor size internal threaded anchor rods					IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Steel failure[1]										
Characteristic tension resistance, Steel, strength class	5.8		$N_{Rk,s}$	[kN]	10	17	29	42	76	123
	8.8		$N_{Rk,s}$	[kN]	16	27	46	67	121	196
Partial factor, strength class 5.8 and 8.8			$\gamma_{Ms,N}$	[-]	1,5					
Characteristic tension resistance, Stainless Steel A4 and HCR, Strength class 70 [2]			$N_{Rk,s}$	[kN]	14	26	41	59	110	124
Partial factor			$\gamma_{Ms,N}$	[-]	1,87					2,86
Combined pull-out and concrete cone failure										
Characteristic bond resistance in non-cracked concrete C20/25										
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	12	12	12	12	11	9
	II: 80°C/50°C				9	9	9	9	8,5	6,5
	III: 120°C/72°C				6,5	6,5	6,5	6,5	6,5	5,0
	I: 40°C/24°C	flooded bore hole			8,5	8,5	8,5	No Performance Assessed		
	II: 80°C/50°C				6,5	6,5	6,5			
	III: 120°C/72°C				5,0	5,0	5,0			
Characteristic bond resistance in cracked concrete C20/25										
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	5,0	5,5	5,5	5,5	5,5	6,5
	II: 80°C/50°C				3,5	4,0	4,0	4,0	4,0	4,5
	III: 120°C/72°C				2,5	3,0	3,0	3,0	3,0	3,5
	I: 40°C/24°C	flooded bore hole			4,0	5,5	5,5	No Performance Assessed		
	II: 80°C/50°C				3,0	4,0	4,0			
	III: 120°C/72°C				2,5	3,0	3,0			
Reduktion factor ψ^0_{sus} in cracked and non-cracked concrete C20/25										
Temperature range	I: 40°C/24°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,73					
	II: 80°C/50°C				0,65					
	III: 120°C/72°C				0,57					
Increasing factors for concrete ψ_c			C25/30		1,02					
			C30/37		1,04					
			C35/45		1,07					
			C40/50		1,08					
			C45/55		1,09					
			C50/60		1,10					
Concrete cone failure										
Relevant parameter					see Table C2					
Splitting failure										
Relevant parameter					see Table C2					
Installation factor										
for dry and wet concrete			γ_{inst}	[-]	1,2					
for flooded bore hole					1,4			No Performance Assessed		

[1] Fastenings (incl. nut and washer) must comply with the appropriate material and property class of the internal threaded rod. The characteristic tension resistance for steel failure is valid for the internal threaded rod and the fastening element.

[2] For IG-M20 strength class 50 is valid

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete	**Annex C 5**
Performances Characteristic values of tension loads under static and quasi-static action	

Table C6: Characteristic values of shear loads under static and quasi-static action

Anchor size for internal threaded anchor rods				IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Steel failure without lever arm[1)]									
Characteristic shear resistance, Steel, strength class	5.8	$V^0_{Rk,s}$	[kN]	5	9	15	21	38	61
	8.8	$V^0_{Rk,s}$	[kN]	8	14	23	34	60	98
Partial factor, strength class 5.8 and 8.8		$\gamma_{Ms,V}$	[-]	1,25					
Characteristic shear resistance, Stainless Steel A4 and HCR, Strength class 70[2)]		$V^0_{Rk,s}$	[kN]	7	13	20	30	55	40
Partial factor		$\gamma_{Ms,V}$	[-]	1,56					2,38
Ductility factor		k_7	[-]	1,0					
Steel failure with lever arm[1)]									
Characteristic bending moment, Steel, strength class	5.8	$M^0_{Rk,s}$	[Nm]	8	19	37	66	167	325
	8.8	$M^0_{Rk,s}$	[Nm]	12	30	60	105	267	519
Partial factor, strength class 5.8 and 8.8		$\gamma_{Ms,V}$	[-]	1,25					
Characteristic bending moment, Stainless Steel A4 and HCR, Strength class 70[2)]		$M^0_{Rk,s}$	[Nm]	11	26	52	92	233	456
Partial factor		$\gamma_{Ms,V}$	[-]	1,56					2,38
Concrete pry-out failure									
Factor		k_8	[-]	2,0					
Installation factor		γ_{inst}	[-]	1,0					
Concrete edge failure									
Effective length of fastener		l_f	[mm]	$\min(h_{ef};\ 12 \cdot d_{nom})$					$\min(h_{ef};\ 300mm)$
Outside diameter of fastener		d_{nom}	[mm]	10	12	16	20	24	30
Installation factor		γ_{inst}	[-]	1,0					

[1)] Fastenings (incl. nut and washer) must comply with the appropriate material and property class of the internal threaded rod. The characteristic tension resistance for steel failure is valid for the internal threaded rod and the fastening element.
[2)] For IG-M20 strength class 50 is valid

Table C7: Characteristic values of tension loads under static and quasi-static action

Anchor size reinforcing bar				**Ø 8**	**Ø 10**	**Ø 12**	**Ø 14**	**Ø 16**	**Ø 20**	**Ø 25**	**Ø 28**	**Ø 32**
Steel failure												
Characteristic tension resistance		$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$ [1]								
Cross section area		A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor		$\gamma_{Ms,N}$	[-]	1,4 [2]								
Combined pull-out and concrete failure												
Characteristic bond resistance in non-cracked concrete C20/25												
Temperature range I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	10	12	12	12	12	12	11	10	8,5
Temperature range II: 80°C/50°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	7,5	9	9	9	9	9	8,0	7,0	6,0
Temperature range III: 120°C/72°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	5,5	6,5	6,5	6,5	6,5	6,5	6,0	5,0	4,5
Temperature range I: 40°C/24°C	flooded bore hole	$\tau_{Rk,ucr}$	[N/mm²]	7,5	8,5	8,5	8,5	8,5	No Performance Assessed			
Temperature range II: 80°C/50°C	flooded bore hole	$\tau_{Rk,ucr}$	[N/mm²]	5,5	6,5	6,5	6,5	6,5				
Temperature range III: 120°C/72°C	flooded bore hole	$\tau_{Rk,ucr}$	[N/mm²]	4,0	5,0	5,0	5,0	5,0				
Characteristic bond resistance in cracked concrete C20/25												
Temperature range I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	4,0	5,0	5,5	5,5	5,5	5,5	5,5	6,5	6,5
Temperature range II: 80°C/50°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	2,5	3,5	4,0	4,0	4,0	4,0	4,0	4,5	4,5
Temperature range III: 120°C/72°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	2,0	2,5	3,0	3,0	3,0	3,0	3,0	3,5	3,5
Temperature range I: 40°C/24°C	flooded bore hole	$\tau_{Rk,cr}$	[N/mm²]	4,0	4,0	5,5	5,5	5,5	No Performance Assessed			
Temperature range II: 80°C/50°C	flooded bore hole	$\tau_{Rk,cr}$	[N/mm²]	2,5	3,0	4,0	4,0	4,0				
Temperature range III: 120°C/72°C	flooded bore hole	$\tau_{Rk,cr}$	[N/mm²]	2,0	2,5	3,0	3,0	3,0				
Reduktion factor ψ^0_{sus} in cracked and non-cracked concrete C20/25												
Temperature range I: 40°C/24°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,73								
Temperature range II: 80°C/50°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,65								
Temperature range III: 120°C/72°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,57								
Increasing factors for concrete ψ_c		C25/30		1,02								
		C30/37		1,04								
		C35/45		1,07								
		C40/50		1,08								
		C45/55		1,09								
		C50/60		1,10								
Concrete cone failure												
Relevant parameter				see Table C2								
Splitting												
Relevant parameter				see Table C2								
Installation factor												
for dry and wet concrete		γ_{inst}	[-]	1,2	1,2							
for flooded bore hole		γ_{inst}	[-]	1,4					No Performance Assessed			

[1] f_{uk} shall be taken from the specifications of reinforcing bars
[2] in absence of national regulation

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete	**Annex C 7**
Performances Characteristic values of tension loads under static and quasi-static action	

Table C8: Characteristic values of shear loads under static and quasi-static action

Anchor size reinforcing bar			**Ø 8**	**Ø 10**	**Ø 12**	**Ø 14**	**Ø 16**	**Ø 20**	**Ø 25**	**Ø 28**	**Ø 32**
Steel failure without lever arm											
Characteristic shear resistance	$V^0_{Rk,s}$	[kN]	$0{,}50 \cdot A_s \cdot f_{uk}$ [1)]								
Cross section area	A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor	$\gamma_{Ms,V}$	[-]	1,5 [2)]								
Ductility factor	k_7	[-]	1,0								
Steel failure with lever arm											
Characteristic bending moment	$M^0_{Rk,s}$	[Nm]	$1.2 \cdot W_{el} \cdot f_{uk}$ [1)]								
Elastic section modulus	W_{el}	[mm³]	50	98	170	269	402	785	1534	2155	3217
Partial factor	$\gamma_{Ms,V}$	[-]	1,5 [2)]								
Concrete pry-out failure											
Factor	k_8	[-]	2,0								
Installation factor	γ_{inst}	[-]	1,0								
Concrete edge failure											
Effective length of fastener	l_f	[mm]	$\min(h_{ef};\ 12 \cdot d_{nom})$						$\min(h_{ef};\ 300mm)$		
Outside diameter of fastener	d_{nom}	[mm]	8	10	12	14	16	20	25	28	32
Installation factor	γ_{inst}	[-]	1,0								

[1)] f_{uk} shall be taken from the specifications of reinforcing bars
[2)] in absence of national regulation

Table C9: Displacements under tension load[1] (threaded rod)

Anchor size threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Non-cracked concrete C20/25 under static and quasi-static action										
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,021	0,023	0,026	0,031	0,036	0,041	0,045	0,049
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,030	0,033	0,037	0,045	0,052	0,060	0,065	0,071
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,075	0,088	0,100	0,110	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,108	0,127	0,145	0,159	0,172
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,075	0,088	0,100	0,110	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,108	0,127	0,145	0,159	0,172
Cracked concrete C20/25 under static and quasi-static action										
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,090		0,070					
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,105		0,105					
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219		0,170					
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255		0,245					
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219		0,170					
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255		0,245					

[1] Calculation of the displacement
$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau$; τ: action bond stress for tension
$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$;

Table C10: Displacements under shear load[1] (threaded rod)

Anchor size threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Non-cracked concrete C20/25 under static and quasi-static action										
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,06	0,06	0,05	0,04	0,04	0,03	0,03	0,03
	$\delta_{V\infty}$-factor	[mm/kN]	0,09	0,08	0,08	0,06	0,06	0,05	0,05	0,05
Cracked concrete C20/25 under static and quasi-static action										
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,12	0,12	0,11	0,10	0,09	0,08	0,08	0,07
	$\delta_{V\infty}$-factor	[mm/kN]	0,18	0,18	0,17	0,15	0,14	0,13	0,12	0,10

[1] Calculation of the displacement
$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V$; V: action shear load
$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$;

Table C11: Displacements under tension load[1] (Internal threaded anchor rod)

Anchor size Internal threaded anchor rod			IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Non-cracked concrete C20/25 under static and quasi-static action								
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,023	0,026	0,031	0,036	0,041	0,049
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,033	0,037	0,045	0,052	0,060	0,071
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,056	0,063	0,075	0,088	0,100	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,081	0,090	0,108	0,127	0,145	0,172
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,056	0,063	0,075	0,088	0,100	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,081	0,090	0,108	0,127	0,145	0,172
Cracked concrete C20/25 under static and quasi-static action								
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,090	0,070				
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,105	0,105				
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219	0,170				
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255	0,245				
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219	0,170				
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255	0,245				

[1] Calculation of the displacement
$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau$; τ: action bond stress for tension
$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$;

Table C12: Displacements under shear load[1] (Internal threaded anchor rod)

Anchor size Internal threaded anchor rod			IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Non-cracked and cracked concrete C20/25 under static and quasi-static action								
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,07	0,06	0,06	0,05	0,04	0,04
	$\delta_{V\infty}$-factor	[mm/kN]	0,10	0,09	0,08	0,08	0,06	0,06

[1] Calculation of the displacement
$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V$; V: action shear load
$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$;

Table C13: Displacements under tension load[1] (rebar)

Anchor size reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
Non-cracked concrete C20/25 under static and quasi-static action											
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,021	0,023	0,026	0,028	0,031	0,036	0,043	0,047	0,052
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,030	0,033	0,037	0,041	0,045	0,052	0,061	0,071	0,075
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,069	0,075	0,088	0,104	0,113	0,126
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,099	0,108	0,127	0,149	0,163	0,181
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,069	0,075	0,088	0,104	0,113	0,126
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,099	0,108	0,127	0,149	0,163	0,181
Cracked concrete C20/25 under static and quasi-static action											
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,090		0,070						
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,105		0,105						
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219		0,170						
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255		0,245						
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219		0,170						
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255		0,245						

[1] Calculation of the displacement
$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau$; τ: action bond stress for tension
$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$;

Table C14: Displacement under shear load[1] (rebar)

Anchor size reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
Non-cracked concrete C20/25 under static and quasi-static action											
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,06	0,05	0,05	0,04	0,04	0,04	0,03	0,03	0,03
	$\delta_{V\infty}$-factor	[mm/kN]	0,09	0,08	0,08	0,06	0,06	0,05	0,05	0,04	0,04
Cracked concrete C20/25 under static and quasi-static action											
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,12	0,12	0,11	0,11	0,10	0,09	0,08	0,07	0,06
	$\delta_{V\infty}$-factor	[mm/kN]	0,18	0,18	0,17	0,16	0,15	0,14	0,12	0,11	0,10

[1] Calculation of the displacement
$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V$; V: action shear load
$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$;

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete	**Annex C 11**
Performances Displacements (rebar)	

Table C15: Characteristic values of tension loads under seismic action (performance category C1)

Anchor size threaded rod					M8	M10	M12	M16	M20	M24	M27	M30
Steel failure												
Characteristic tension resistance			$N_{Rk,s,eq,C1}$	[kN]	$1,0 \cdot N_{Rk,s}$							
Partial factor			$\gamma_{Ms,N}$	[-]	see Table C1							
Combined pull-out and concrete failure												
Characteristic bond resistance in non-cracked and cracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	2,5	3,1	3,7	3,7	3,7	3,8	4,5	4,5
	II: 80°C/50°C				1,6	2,2	2,7	2,7	2,7	2,8	3,1	3,1
	III: 120°C/72°C				1,3	1,6	2,0	2,0	2,0	2,1	2,4	2,4
	I: 40°C/24°C	flooded bore hole			2,5	2,5	3,7	3,7	No Performance Assessed			
	II: 80°C/50°C				1,6	1,9	2,7	2,7				
	III: 120°C/72°C				1,3	1,6	2,0	2,0				
Increasing factors for concrete ψ_c			C25/30 to C50/60		1,0							
Installation factor												
for dry and wet concrete			γ_{inst}	[-]	1,0	1,2						
for flooded bore hole					1,4				No Performance Assessed			

Table C16: Characteristic values of shear loads under seismic action (performance category C1)

Anchor size threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Steel failure without lever arm										
Characteristic shear resistance (Seismic C1)	$V_{Rk,s,eq,C1}$	[kN]	$0,70 \cdot V^0_{Rk,s}$							
Partial factor	$\gamma_{Ms,V}$	[-]	see Table C1							
Factor for annular gap	α_{gap}	[-]	0,5 (1,0)[1]							

[1] Value in brackets valid for filled annular gab between anchor and clearance hole in the fixture. Use of special filling washer Annex A 3 is required

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete	**Annex C 12**
Performances Characteristic values of tension loads and shear loads under seismic action (performance category C1)	

Table C17: Characteristic values of tension loads under seismic action (performance category C1)

Anchor size reinforcing bar				**Ø 8**	**Ø 10**	**Ø 12**	**Ø 14**	**Ø 16**	**Ø 20**	**Ø 25**	**Ø 28**	**Ø 32**
Steel failure												
Characteristic tension resistance		$N_{Rk,s,eq,C1}$	[kN]	$1,0 \cdot A_s \cdot f_{uk}$ [1]								
Cross section area		A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor		$\gamma_{Ms,N}$	[-]	1,4 [2]								
Combined pull-out and concrete failure												
Characteristic bond resistance in non-cracked and cracked concrete C20/25												
Temperature range I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	2,5	3,1	3,7	3,7	3,7	3,7	3,8	4,5	4,5
Temperature range II: 80°C/50°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	1,6	2,2	2,7	2,7	2,7	2,7	2,8	3,1	3,1
Temperature range III: 120°C/72°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	1,3	1,6	2,0	2,0	2,0	2,0	2,1	2,4	2,4
Temperature range I: 40°C/24°C	flooded bore hole	$\tau_{Rk,eq,C1}$	[N/mm²]	2,5	2,5	3,7	3,7	3,7	No Performance Assessed			
Temperature range II: 80°C/50°C	flooded bore hole	$\tau_{Rk,eq,C1}$	[N/mm²]	1,6	1,9	2,7	2,7	2,7				
Temperature range III: 120°C/72°C	flooded bore hole	$\tau_{Rk,eq,C1}$	[N/mm²]	1,3	1,6	2,0	2,0	2,0				
Increasing factors for concrete ψ_C		C25/30 to C50/60		1,0								
Installation factor												
for dry and wet concrete		γ_{inst}	[-]	1,2	1,2							
for flooded bore hole		γ_{inst}	[-]	1,4					No Performance Assessed			

[1] f_{uk} shall be taken from the specifications of reinforcing bars
[2] in absence of national regulation

Table C18: Characteristic values of shear loads under seismic action (performance category C1)

Anchor size reinforcing bar			**Ø 8**	**Ø 10**	**Ø 12**	**Ø 14**	**Ø 16**	**Ø 20**	**Ø 25**	**Ø 28**	**Ø 32**
Steel failure without lever arm											
Characteristic shear resistance	$V_{Rk,s,eq,C1}$	[kN]	$0,35 \cdot A_s \cdot f_{uk}$ [2]								
Cross section area	A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor	$\gamma_{Ms,V}$	[-]	1,5 [2]								
Factor for annular gap	α_{gap}	[-]	0,5 (1,0) [3]								

[1] f_{uk} shall be taken from the specifications of reinforcing bars
[2] in absence of national regulation
[3] Value in brackets valid for filled annular gab between anchor and clearance hole in the fixture. Use of special filling washer Annex A 3 is required

EJOT Chemical Anchor MULTIFIX USF, MULTIFIX USF winter for concrete	**Annex C 13**
Performances Characteristic values of tension loads and shear loads under seismic action (performance category C1)	